SG12-80X 12V 80Ah(10hr)

Gel battery shows some distinctive advantages over flooded battery or AGM battery, such as super thermal stability, high deep discharge capability, good recovery from deep discharge, even if the battery is left discharged for three days, it will recover to 100% of capacity. With the above-mentioned advantages, the gel battery has long service life, specially suitable for motive power applications, such as golf trailer, sruubber, folklift,etc. The deep discharge cycles increased 50% as compared with the AGM battery.

Battery Construction


Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	PVC	Gelled acid

General Features

- Nanometer SiO₂ and H₂SO₄ gelled electrolyte technology for efficiency gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- . Long service life, float or cyclic applications.
- Maintenance-free operation.
- · Low self discharge.
- Case and cover avaiable in both standard and flame restardant ABS.

Dimensions and Weight

Length(mm / inch)	330 / 13.0
Width(mm / inch)	171 / 6.73
Height(mm / inch)	215 / 8.46
Total Height(mm / inch)	220 / 8.66
Approx. Weight(Kg / lbs)	29.5 / 65.0



Performance Characteristics

Nominal Voltage	12V
Number of cell	6
Design Life	12 years
Nominal Capacity 77°F(25°C)	
10 hour rate (8.0A, 10.8V)	80.0Ah
5 hour rate (14.1A, 10.5V)	70.5Ah
1 hour rate (49.6A, 9.6V)	49.6Ah
Internal Resistance	

Fully Charged battery 77°F(25°C) 7.0mOhms

Self-Discharge

2% of capacity declined per month at 20°C(average)

Operating Temperature Range

Discharge -20~60°C Charge -10~60°C Storage -20~60°C Max. Discharge Current 77°F(25°C) 750A(5s) **Short Circuit Current** 1900A Charge Methods: Constant Voltage Charge 77°F(25°C) Cycle use 14.4-14.7V Maximum charging current 24.0A Temperature compensation -20mV/°C Standby use 13.5-13.8V

No charge current limit is required

Temperature compensation -30mV/°C

Discharge Constant Current (Amperes at 77°F25°C)

End point volts/cell	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	168	138	80.0	49.6	20.8	15.2	8.40	4.48
1.65V	158	128	78.4	48.0	20.3	14.7	8.32	4.40
1.70V	149	122	76.8	46.4	19.7	14.4	8.16	4.32
1.75V	139	112	75.2	44.8	19.5	14.1	8.08	4.28
1.80V	130	102	72.0	42.4	18.7	13.6	8.00	4.20

Discharge Constant Power (Watts at 77°F25°C)

2.00.10.90 00.10.10.11.11.01.01.11.1.1.20.07								
End point volts/cell	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	288	233	150	92.9	38.9	29.2	16.3	8.82
1.65V	274	231	143	88.3	37.0	27.6	15.4	8.31
1.70V	267	222	136	84.6	35.0	26.3	14.5	7.95
1.75V	254	208	132	81.7	33.3	25.7	14.0	7.67
1.80V	241	197	127	78.0	31.4	23.9	13.1	7.39

(Note)The above characteristics data are average values obtained within three charge/discharge cycles not the mimimum values.

SG12-80X 12V 80Ah

